

## SAM™ data sheet SAM-940-5-x-1ps, $\lambda = 940$ nm

Laser wavelength	$\lambda = 940$ nm
High reflection band (R > 93%)	$\lambda = 920 \dots 990$ nm
Absorbance	$A_0 = 5$ %
Modulation depth	$\Delta R = 3$ %
Non-saturable loss	$A_{ns} = 2$ %
Saturation fluence	$\Phi_{sat} = 60 \mu\text{J}/\text{cm}^2$
Relaxation time constant	$\tau \sim 1$ ps
Chip area	4mm x 4mm; other dimensions on request
Chip thickness	400 $\mu\text{m}$
Protection	the SAM is protected with a dielectric front layer
Mounting of SAM-940-5- <b>x</b> -1ps	denotes the type of mounting as follows:
<b>x</b> = 0	unmounted
<b>x</b> = 12.7 g	glued on a copper heat sink with 12.7 mm $\varnothing$
<b>x</b> = 25.4 g	glued on a copper heat sink with 25.4 mm $\varnothing$
<b>x</b> = 12.7 s	soldered on a copper heat sink with 12.7 mm $\varnothing$
<b>x</b> = 25.4 s	soldered on a copper heat sink with 25.4 mm $\varnothing$
<b>x</b> = 25.0 h	soldered on a water cooled copper heat sink with 25.0 mm $\varnothing$
<b>x</b> = FC	mounted on a 1 m singlemode fiber cable with FC connector

### low intensity spectral reflectance

