L-Band Erbium Doped Fibers



Nufern high performance L-Band Erbium-doped fibers are designed for use in L-band amplifiers and compact ASE sources. The 80 µm version is a reduced-cladding fiber ideal for small form-factor devices. All Nufern erbium-doped fibers are fabricated with a proprietary doping technology and have highly consistent and reproducible spectroscopy, ensuring intra-lot and lot-to-lot uniformity. These fibers are extensively characterized and accompanied by lot specific data.

Typical Applications

- L-band amplifiers
- Compact ASE sources
- Small form factor packages

Features & Benefits

- Highly consistent and reproducible spectroscopy no need to batch matching GFFs
- Excellent core concentricity low splice loss
- Detailed lot-specific characterization data compatible with modeling programs

Optical Specifications

Operating Wavelength Core NA Mode Field Diameter Cutoff Core Attenuation Core Absorption

EDFL-980-HP

1565 - 1625 nm 0.250 5.5 ± 0.5 um @ 1550 nm $920 \pm 50 \text{ nm}$ ≤ 15.0 dB/km @ 1200 nm

 $25.0 \pm 2.0 \text{ dB/m near } 1530$ $18.5 \pm 11.5 \, dB/m \, near \, 980$

EDFL-980-HP-80

1565 - 1625 nm 0.250 $5.5 \pm 0.5 \, \text{um} \ @ \ 1550 \, \text{nm}$ $920 \pm 50 \text{ nm}$ ≤ 15.0 dB/km @ 1200 nm $25.0 \pm 2.0 \text{ dB/m near } 1530$

 $18.5 \pm 11.5 \, dB/m \, near \, 980$ nm

EDFL-1480-HP

1565 - 1625 nm 0.250

5.3 ± 0.5 µm @ 1550 nm

 $1420 \pm 50 \text{ nm}$

≤ 15.0 dB/km @ 1200 nm $15.0 \pm 3.0 \, dB/m$ at 980 nm $30.0 \pm 3.0 \, dB/m \, near \, 1530$ nm

Geometrical & Mechanical Specifications

Cladding Diameter Core Diameter Coating Diameter Coating Concentricity Core/Clad Offset Coating Material Operating Temperature Range Prooftest Level

 $125.0 \pm 1.0 \, \text{um}$ 2.8 µm $245.0 \pm 10.0 \, \mu m$ $< 5.0 \ \mu m$ ≤ 0.30 µm UV Cured, Dual Acrylate

-40 to 85 °C \geq 200 kpsi (1.4 GN/m²)

 $80.0 \pm 1.0 \, \text{um}$ $2.8 \, \mu m$ $165.0 \pm 10.0 \, \mu m$ < 5.0 µm ≤ $0.30 \, \mu m$

UV Cured, Dual Acrylate -40 to 85 °C ≥ 200 kpsi (1.4 GN/m²) 125.0 ± 1.0 um $4.5 \, \mu m$ $245.0 \pm 10.0 \, \mu m$

 $< 5.0 \ \mu m$ $\leq 0.30 \, \mu m$

UV Cured, Dual Acrylate -40 to 85 °C ≥ 200 kpsi (1.4 GN/m²)



