

400 Micron Core Power Delivery Fibers

Nufern's specialty multimode step-index fibers are designed for compatibility with the majority of fiber-coupled, bar and stack diode-laser packages and support the diode laser power delivery market. These power delivery fibers are available in 400/440 and 400/480 core/clad ratios in low and high NA versions. The 400/480 has a low refractive index fluoroacrylate coating for added power confinement. Other fiber diameters are available upon request.

Typical Applications

- · Fiber coupled diode lasers
- Couplers and pump combiners

Features & Benefits

- 0.12 and 0.22 NA Compatible with majority of fiber-coupled, diode-laser packages
- Exceptional geometric uniformity and core/clad concentricity Ease of coupling to pump diodes

Op	tic	al :	Sp	ec	ifi	ca	tio	ns
-----------	-----	------	----	----	-----	----	-----	----

Operating Wavelength Core NA First Cladding NA (5%) OH Level

MM-S400/440-12A

800 - 1600 nm 0.120 ± 0.020 N/A Low

MM-S400/440-22A

800 - 1600 nm 0.220 ± 0.020 N/A Low

MM-S400/480-22FA

800 - 1600 nm 0.220 ± 0.020 ≥ 0.46 Low

Geometrical & Mechanical Specifications

Cladding Diameter Core Diameter Coating Diameter Core/Clad Offset Coating Material Prooftest Level $440.0 \pm 8.0 \, \mu m$ ≤ 5.00 µm

 $400.0 \pm 9.0 \, \mu m$ $625.0 \pm 25.0 \, \mu m$ UV Cured, Dual Acrylate ≥ 100 kpsi (0.7 GN/m²)

$440.0 \pm 8.0 \, \mu m$ $400.0 \pm 9.0 \, \mu m$ $625.0 \pm 25.0 \, \mu m$ ≤ 5.00 µm UV Cured, Dual Acrylate ≥ 100 kpsi (0.7 GN/m²)

$480.0 \pm 8.0 \, \mu m$ $400.0 \pm 9.0 \, \mu m$ $640.0 \pm 25.0 \, \mu m$ ≤ 5.00 µm Low Index Polymer ≥ 100 kpsi (0.7 GN/m²)



