5/130 Passive Double Clad Fibers



Nufern's general purpose passive double-clad fiber is available in two-versions — PANDA-style, polarization-maintaining (PM) and non-PM. Designed specifically to work with 5/130 Yb-doped active fibers for CW applications at lower powers, ensuring low loss and improved splice compatability. These fibers' telecom-type geometrics are compatible with readily available low-cost pump diodes and fiber-based components. They utilize the latest fiber design and NuCOATTM coating technology to ensure excellent preservation of beam quality and extended operating life demanded by today's industrial fiber laser applications.

Typical Applications

- · Laser marking
- Fiber amplifier pumps
- IR sources for frequency doubling

Features & Benefits

- NuCOAT™ fluoroacrylate coating Greater fiber durability in extreme environmental operating & storage conditions
- Low cost double-clad technology Enables use of high power multimode pump diodes
- Single-mode output Compatiable with standard telecom 980/1060 nm fiber-based components
- PANDA-style stress structure Linearly polarized output for frequency conversion"

Optical Specifications

Operating Wavelength (nominal) Core NA First Cladding NA (5%)

Mode Field Diameter

Cutoff

Core Attenuation
Cladding Attenuation

Birefringence

PM-GDF-5/130

SM-GDF-5/130

1060 nm 1060 nm 0.120 0.120 ≥ 0.46 ≥ 0.46

 $6.5 \pm 0.5 \ \mu m \ @ \ 1060 \ nm$ $6.5 \pm 0.5 \ \mu m \ @ \ 1060 \ nm$

 $950 \pm 50 \text{ nm}$ $950 \pm 50 \text{ nm}$

≤ 10.0 dB/km @ 1200 nm ≤ 15.0 dB/km @ 1095 nm ≤ 15.0 dB/km @ 1095 nm

 2.5×10^{-4} N/A

Geometrical & Mechanical Specifications

Cladding Diameter
Core Diameter
Coating Diameter
Coating Concentricity
Core/Clad Offset
Prooftest Level

 $130.0 \pm 1.0 \ \mu m$ $130.0 \pm 1.0 \ \mu m$ $5.0 \ \mu m$ $5.0 \ \mu m$ $245.0 \pm 10.0 \ \mu m$

< 5.0 μm < 5.0 μm < 5.0 μm ≤ 1.00 μm

 \geq 100 kpsi (0.7 GN/m²) \geq 100 kpsi (0.7 GN/m²)





