

Visible Wavelength Select Cutoff Single-Mode Fibers

Nufern visible wavelength fibers are optimized for use from 400 up to 900 nm. The high-performance fibers were developed for applications such as RGB components requiring generation of couplers, diode pigtails and unique delivery needs. These fibers feature greater proof test levels and a tigher second mode cutoff tolerance than standard fibers, resulting in higher strength, increased component reliability, better production yields and reduced costs for component manufacturers.

Typical Applications

- · Diode Pigtails
- · Compact UV sources
- · RGB components
- Couplers

Features & Benefits

- Superior fiber geometrical tolerances Improved connectorization and coupling performance
- Extremely tight second mode cutoff tolerance Enhanced component reproducibility
- Higher proof test level Greater reliability for tight bend applications

Optical	Specifi	cations
---------	---------	---------

Operating Wavelength Core NA Mode Field Diameter Mode Field Diameter (Gaussian) Cutoff

Core Attenuation

405-HP

400 – 550 nm 0.130 N/A 3.5 ± 0.5 μm @ 5

 $3.5 \pm 0.5 \,\mu\text{m} @ 515 \,\text{nm}$ $370 \pm 20 \,\text{nm}$ $\leq 30.0 \,\text{dB/km} @ 515 \,\text{nm}$

≤ 12.0 dB/km @ 630 nm

460-HP

450 – 600 nm 0.130 N/A

 $3.5 \pm 0.5 \,\mu\text{m} @ 515 \,\text{nm}$ $430 \pm 20 \,\text{nm}$ $\leq 12.0 \,\text{dB/km} @ 630 \,\text{nm}$

≤ 30.0 dB/km @ 515 nm

570 ± 30 nm ≤ 12.0 dB/km @ 630 nm

630-HP

0.130

600 - 770 nm

Geometrical & Mechanical Specifications

Cladding Diameter
Core Diameter
Coating Diameter
Coating Concentricity
Core/Clad Offset
Coating Material
Operating Temperature Range
Short Term Bend Radius
Long Term Bend Radius
Prooftest Level

125.0 ± 1.0 μm 2.1 μm 245.0 ± 15.0 μm < 5.0 μm

> ≤ 0.50 µm UV Cured, Dual Acrylate -55 to 85 °C ≥ 6 mm

≥ 13 mm ≥ 200 kpsi (1.4 GN/m²) 125.0 ± 1.0 μm 2.5 μm

 $245.0 \pm 15.0 \,\mu \text{m}$ < $5.0 \,\mu \text{m}$ $\leq 0.50 \,\mu \text{m}$

UV Cured, Dual Acrylate -55 to 85 °C ≥ 6 mm

 \geq 13 mm l/m^2 \geq 200 kpsi (1.4 GN/m²)

125.0 ± 1.0 μm

3.5 µm 245.0 ± 15.0 µm < 5.0 µm

UV Cured, Dual Acrylate -55 to 85 °C

≥ 6 mm ≥ 13 mm

 $\leq 0.50 \, \mu \text{m}$

≥ 200 kpsi (1.4 GN/m²)



