

Short Wavelength Pure Silica Core Polarization Maintaining Fibers

Nufern's industry leading short wavelength pure silica core polarization maintaining fibers have superior waveguide, radiation, and mechanical properties, enabling a large variety of applications in diverse markets. High consistency and extreme end-to-end control of optical properties provide particular advantage in spectrographic and frequency sensitive applications. The pure silica core fiber is optimum for demanding applications in the UV and visible spectrum requiring ultra-low attenuation over longer lengths and where resistance to radiation-induced damage and color center formation are critical

Typical Applications

- · Laser pigtailing
- Spectroscopy
- Sensors
- · Bio-medical
- Metrology

Features & Benefits

- Panda-style configuration Superior optical performance, intrinsically good radiation performance
- Tight specifications Highly deterministic results, highest product yield

PM-S630-HP

- High proof test Low risk of mechanical damage and failure
- High fatigue failure resistance Longest service life
- Pure silica core Resistance to radiation-induced damage and color center formation

Optical Specifications

Operating Wavelength Core NA Mode Field Diameter (Gaussian)

Cutoff

Core Attenuation
Beat Length (nominal)
Birefringence

Geometrical & Mechanical Specifications

Cladding Diameter
Core Diameter
Coating Diameter
Coating Concentricity
Core/Clad Offset
Coating Material
Operating Temperature Range
Prooftest Level

PM-S460-HP

460 – 550 nm 630 – 780 nm 0.120 0.120

 $3.5 \pm 0.3 \ \mu m$ @ 460 nm $4.2 \pm 0.5 \ \mu m$ @ 630 nm

 $420 \pm 30 \text{ nm}$ $580 \pm 40 \text{ nm}$

 \leq 30.0 dB/km @ 460 nm \leq 12.0 dB/km @ 630 nm 2.3 mm @ 460 nm 4.7 mm @ 630 nm nominal 2×10^{-4} nominal 1.3×10^{-4}

 $125.0 \pm 1.0 \, \mu m$ $125.0 \pm 1.0 \, \mu m$
 $3.0 \, \mu m$ $3.5 \, \mu m$
 $245.0 \pm 15.0 \, \mu m$ $245.0 \pm 15.0 \, \mu m$
 $< 5.0 \, \mu m$ $< 5.0 \, \mu m$
 $\leq 0.50 \, \mu m$ $\leq 0.50 \, \mu m$

UV Cured, Dual Acrylate UV Cured, Dual Acrylate

-40 to 85 °C -40 to 85 °C

 \geq 200 kpsi (1.4 GN/m²) \geq 200 kpsi (1.4 GN/m²)



